

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (previously presented): A butadiene-based polymer having a 1,3-butadiene monomer unit, characterized in that a cis-1,4 bond content and a vinyl bond content in the 1,3-butadiene monomer unit as measured by a Fourier transform infrared spectroscopy (FT-IR) and calculated according to the following equations (IV) and (VI) are not less than 98.0% and not more than 0.3%, respectively, and a ratio (Mw/Mn) of weight average molecular weight (Mw) to number average molecular weight (Mn) is 1.6-3.5,

$$(\text{cis-1,4 bond content}) = e/(e+f+g) \times 100 (\%) \quad \dots \dots (IV)$$

$$(\text{vinyl bond content}) = g/(e+f+g) \times 100 (\%) \quad \dots \dots (VI)$$

wherein e, f and g are derived from the following matrix (III):

$$\begin{bmatrix} 1.7455 & 0 & -0.0151 \\ -0.0454 & 0.4292 & -0.0129 \\ -0.007 & 0 & 0.3746 \end{bmatrix} \begin{bmatrix} \log_{10}(a/d) \\ \log_{10}(a/b) \\ \log_{10}(a/c) \end{bmatrix} = \begin{bmatrix} e \\ f \\ g \end{bmatrix} \quad \dots \dots (III)$$

wherein a represents a mountain peak value near 1130 cm^{-1} , b represents a valley peak value near 967 cm^{-1} , c represents a valley peak value near 911 cm^{-1} and d represents a valley peak value near 736 cm^{-1} in the FT-IR spectrum.

2. (original): A butadiene-based polymer according to claim 1, wherein the cis-1,4 bond content and the vinyl bond content satisfy a relationship of the following equation (I):

$$(\text{vinyl bond content}) \leq 0.25 \times ((\text{cis-1,4 bond content}) - 97) (\%) \cdots \cdots (I)$$

3. (original): A butadiene-based polymer according to claim 1, wherein the ratio (Mw/Mn) of weight average molecular weight (Mw) to number average molecular weight (Mn) is 1.6-2.7.

4. (original): A butadiene-based polymer according to claim 1, wherein the polymer consists of 80-100% by mass of 1,3-butadiene monomer unit and 20-0% by mass of the other monomer unit capable of copolymerizing with 1,3-butadiene.

5. (original): A butadiene-based polymer according to claim 4, wherein the polymer is made of only 1,3-butadiene monomer unit.

6. (original): A butadiene-based polymer according to claim 1, wherein the number average molecular weight (Mn) is 100,000-500,000.


7. (original): A butadiene-based polymer according to claim 6, wherein the number average molecular weight (Mn) is 150,000-300,000.

8. (currently amended): A method of producing a butadiene-based polymer, characterized in that monomers at least containing 1,3-butadiene are polymerized through a

solution polymerization at a temperature of lower than 25°C in the presence of a catalyst system consisting of:

(A) component: a compound containing a rare earth element of Atomic Number 57-71 in the Periodic Table or a reaction product of such a compound with a Lewis base;

(B) component: an organoaluminum compound represented by the following general formula (II):



(wherein R^1 and R^2 are the same or different and are hydrocarbon group having a carbon number of 1-10 or a hydrogen atom, and R^3 is a hydrocarbon group having a carbon number of 1-10 provided that R^3 may be the same as or different from R^1 or R^2) and/or (D) component: an aluminoxane;

(C) component: at least one of Lewis acid, a complex compound of a metal halogen compound and Lewis base and an organic compound containing an active halogen, and

a conjugated diene monomer, and

the catalyst system is previously prepared in the presence of component (A), component (B) and/or component (D), component (C), and the conjugated diene monomer,

wherein the rare earth element containing compound in the component (A) is a branched carboxylate of neodymium soluble in a hydrocarbon solvent or a reaction product of such a salt with a Lewis base soluble in a hydrocarbon solvent.

9-12. (canceled).

13. (previously presented): A rubber composition, characterized in that a rubber component contains not less than 10% by mass of a butadiene-based polymer as claimed in claim 1.

14. (original): A rubber composition according to claim 13, wherein less than 10 parts by mass of a filler is compounded based on 100 parts by mass of the rubber component.

15. (original): A rubber composition according to claim 14, wherein the rubber composition is sulfur crosslinkable.

16. (previously presented): A tire, characterized in that a rubber composition as claimed in claim 13 is used in any member of the tire.

17. (canceled).

18. (canceled).